



Material	Br		bHc		i H c		(BH) max		Density	Tw
	KGs	mT	Koe	KA/ m	Koe	KA/ m	MGOe	KJ/ m <sup>3</sup>	g/ cm <sup>3</sup>	C°
N30	10.8	1.080	10.5	836	12	955	29	230	7.5	80
N35	11.8	1.180	10.5	836	12	955	34	270	7.5	80
N38	12.2	1.220	10.5	836	12	955	38	295	7.5	80
N40	12.6	1.260	10.5	836	12	955	39	315	7.5	80
N42	13.0	1.300	10.5	836	12	955	41	328	7.5	80
N45	13.5	1.350	10.5	836	12	955	44	352	7.5	80
N48	13.7	1.370	10.5	836	12	955	48	384	7.5	90
N50	14.0	1.400	10.5	836	12	955	50	400	7.5	90
N27H	10.5	1.050	10.5	836	16	1.273	27	210	7.5	120
N30H	11.0	1.100	10.5	836	16	1.273	29	232	7.5	120
N33H	11.5	1.150	10.5	836	16	1.273	31	250	7.5	120
N35H	11.9	1.190	10.5	836	16	1.273	34	275	7.5	120
N38H	12.3	1.230	10.5	836	16	1.273	37	298	7.5	120
N40H	12.6	1.260	10.5	836	16	1.273	39	312	7.5	120
N42H	13.0	1.300	10.5	836	16	1.273	41	329	7.5	120
N46H	13.5	1.350	10.5	836	17	1.352	46	368	7.5	120
N48H	13.7	1.370	10.5	836	17	1.352	48	385	7.5	120
N27SH	10.5	1.050	10.5	836	19	1.513	26	210	7.5	150
N30SH	11.0	1.100	10.5	836	19	1.513	29	232	7.5	150
N33SH	11.5	1.150	10.5	836	19	1.513	31	250	7.5	150
N35SH	11.9	1.190	10.5	836	19	1.513	34	275	7.5	150
N35SH	12.3	1.230	10.5	836	19	1.513	37	295	7.5	150
N40SH	12.6	1.260	10.5	836	19	1.513	39	310	7.5	150
N42SH	13.0	1.300	10.5	836	20	1.592	42	333	7.5	150
N44SH	13.3	1.330	10.5	836	20	1.592	44	349	7.5	150
N28UH	10.5	1.050	09.6	764	25	1.990	27	215	7.5	180
N30UH	11.0	1.100	10.2	812	25	1.990	29	230	7.5	180
N33UH	11.5	1.150	10.5	836	25	1.990	32	255	7.5	180
N38UH	12.2	1.220	10.5	836	25	1.990	38	302	7.5	180
N40UH	12.4	1.240	10.5	836	25	1.990	40	318	7.5	180
N28EH	10.6	1.060	09.8	780	30	2.388	27	215	7.5	200
N30EH	11.0	1.100	10.2	812	30	2.388	29	230	7.5	200
N33EH	11.5	1.150	10.3	820	30	2.388	32	255	7.5	200
N35EH	11.7	1.170	10.5	835	30	2.388	35	278	7.5	200
N38EH	12.2	1.220	10.5	835	30	2.388	38	300	7.5	200