



Magnetic Values plastic bonded Ferrite magnets

■ Specification:

Material	Br	bHc	i H c	(BH) max	Density	Tw
	mT	KA/ m	KA/ m	KJ/ m ³	g/ cm ³	max C°
HF 3/ 18p	135	85	175	3	3,3	130
HF 9/ 19p	215	145	195	9	3,3	130
HF 12/ 22p	250	175	230	12	3,4	130
HF 14/ 19p	275	180	205	14	3,6	130
HF 14/ 23p	275	190	240	14	3,6	130
HF 16/ 19p	290	185	195	16	3,7	130